



DESCRIPTION

The solar protection film EXT 600 was designed in order to significantly reduce heat and glare from the sun once applied on windows. Unlike conventional glare-reducing materials, EXT 600 has non-refle...

[read More](#)

Durability: from 12 to 15 years for vertical application in central Europe.

Use: Réfectiv window films are designed for use on any type of clear normal glass

Maintenance after 30 days: with usual cleaning solutions (non-abrasive, without ammonia...). Cleaning products that may scratch the film should be avoided.

Storage: 2 years from delivery. This film should be kept away from excessive humidity and sun rays, at temperatures below 38°C.

Application Method

The glass surface to be glued on has to be free from dust, grease or other contaminants. Some specific materials such as polycarbonate can cause air bubble problems. Therefore, a compatibility test is recommended. For more precision we recommend to [refer back to the application table](#).

Production and standards

In order to constantly improve our production we may change a product colour and manufacturing process without prior notice. Before applying our products we recommend that our users ensure that the film is suitable for the intended use and comply with current standards.

Material : PET 36 microns
Adhesive: Acrylic polymer
Liner : Siliconed PET 23 microns
Color : Metalized Silver
Application : External & Internal
Warranty : 10 ans years for vertical application in Central Europe
Solar factor G : 48 %
Total Solar Reflection : 52 %
Total Solar Absorption : 19 %
Total Solar Transmission : 43 %
Total Rejected Solar Energy : 52 %
UVA Transmission : 10 %
Application T° : Min. + 5°C
Fire rating: B-s1,d0
Standards : EUROCLASSES

Dimensions (of rolls) :

1.22 x 2.5 m
1.22 x 10 m
1.22 x 30 m

In order to maintain the high level of quality, we do not recommend mixing different film productions when applying films