

Technical Information

PLEXIGLAS® Textures

Extruded (XT)

Product

PLEXIGLAS® Textures are extruded polymethyl methacrylate (PMMA) sheets. Their textured surface is produced by an embossed calender roll. Combined with LEDs, the light-guiding/light-diffusing surfaces create intriguing lighting effects.

The Bark "B" and Ribbed "R" textures run parallel to the sheet length, in the direction of extrusion. Extruded textured sheets are only covered with masking film on the smooth side. Sheets with textures on both sides have no surface masking.

Properties

Besides the general properties of PLEXIGLAS® like

- Excellent light transmission and brilliance
- Outstanding weather resistance
- 100% recycling ability
- Easy to fabricate
- High surface hardness
- Light weight – half the weight of glass
- 11 times more break resistant than glass

PLEXIGLAS® Textures possesses the following properties:

- Light diffusing surface
- From 8mm thickness, suitable for overhead glazing in accordance with DIN EN 356
- Insensitive to scratches

Applications

Due to these properties PLEXIGLAS® Textures are suitable for the following applications

- Lighting applications (standard lamps, ceiling lights, pendant lamps, street lighting); ambient lighting
- Furniture, exhibition booths and store fixtures (counter paneling, shelf partitions, displays)
- Private construction (balcony glazing, door/gate infill panels)

Processing

PLEXIGLAS® Textures can be machined with the same parameters and equipment as standard PLEXIGLAS®. The following fabricating guidelines are available:

- Machining of PLEXIGLAS® (No. 311-1)
- Forming of PLEXIGLAS® (No. 311-2)
- Joining of PLEXIGLAS® (No. 311-3)
- Surface treatment of PLEXIGLAS® (No. 311-4)
- Fabricating tips of PLEXIGLAS® solid sheets (No. 311-5)

Technical data

	Unit	Test standard	PLEXIGLAS® XT
Max. permanent service temperature	°C		70
Forming temperature	°C		150 ... 160
Coefficient of linear thermal expansion a for 0 ... 50 °C	1/K (mm/m °C)	DIN 53752-A	7 * 10 ⁻⁵ (0,07)
Building material class (according to Baustoffklasse DIN 4102)	–	DIN 4102	B2
Combustion behavior	–	BS 476/Part 7+6 BS 2782, Method 508 A DIN EN 13501	Class 3 TP(b) E

For further typical data of PLEXIGLAS® Textures please see the Technical Information of PLEXIGLAS® GS/XT (211-1).

Product range

PLEXIGLAS® Textures is available in the following grades and sizes:

Surface	Grade	Thickness	Size
Z, R, W, P, B, E, CL (on both sides), TK (on both sides)	0A000, 8A470, 7A007	3mm, 4mm, 6mm	2050mm x 1650mm 2500mm x 1650mm 3050mm x 1650mm 3050mm x 2050mm

For details please refer to the PLEXIGLAS® sales handbook.

® = registered trademark PLEXIGLAS is a registered trademark of Evonik Röhm GmbH, Darmstadt, Germany.
Certified to DIN EN ISO 9001 (Quality) and DIN EN ISO 14001 (Environment)

Evonik is a worldwide manufacturer of PMMA products sold under the PLEXIGLAS® trademark on the European, Asian, African and Australian continents and under the ACRYLITE® trademark in the Americas.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Performance Materials GmbH

Acrylic Polymers

Kirschenallee, 64293 Darmstadt, Germany

info@plexiglas.net www.plexiglas.net www.evonik.com

Ref. No. 232-30 July 2015